

TAPE ADHESION

TAPE ADHESION TEST PARAMETERS

- 10 DAYS @ 40°C IN 100% RH CHAMBER
- CROSS HATCH CUT IN COATING - SEE BLUE CIRCLES BELOW
- TAPE PULL 1 HOUR AFTER REMOVAL

RESULTS

- NO REMOVAL OF COATING



NYSHIELD™ GMW 3044 FINISH

TAPE ADHESION (GMW14829)



CONFIDENTIAL