

Tape Adhesion



Tape Adhesion Test Parameter*

- 10 day @ 40°C in 100% RH chamber
- Cross hatch cut through coating
- Scotch tape #898 used
- Tape pull 1 hr after removal

Results

- No removal of coating
- NyShield® has excellent adhesion to the fastener substrate



NYSHIELD® OVER ELECTROPLATE ZN NI FINISH

CONTROLLED RELATIVE HUMIDITY CHAMBER



*GMW 14829